



## 40150 High Temp Gray

### PRODUCT INFORMATION:

40150 High Temp Gray is designed for use in the repair of automotive, marine, and other fiberglass and metal items where a higher heat distortion temperature is needed than standard putties can provide.

### GENERAL PROPERTIES:

Viscosity:	Non-flowing Paste
Catalyst:	BPO Paste
Shelf Life:	1 year (stored out of sun)
Pot Life:	4 to 6 minutes with 2% BPO Paste (50%) at 76 deg. F.
Weight/Gallon:	12.5 to 13 pounds
Sp. Gr.	1.52 to 1.57
Chemically:	Polyester resin and fillers

### USES FOR 40150 High Temp Gray

- Automotive
- Power craft (OEM and repair)
- Sailboats
- Yachts
- Mobile homes
- Travel trailers
- Truck cab
- Tooling
- Most other fiberglass applications

Notice: This information is presented in good faith, but no warranty expressed or implied is given. The information, to our best knowledge, is true and accurate, but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control.

Revised April 2015

DBF, Inc. 18576 Krause PO Box 2385 Riverview, MI 48193  
Phone: 734-285-1480 Fax: 734-285-1481 Website: [dbf-inc.com](http://dbf-inc.com) Email: [custserv@dbf-inc.com](mailto:custserv@dbf-inc.com)