



60701

Product Information

60701 is a lower viscosity, thixotropic polyester compound that spreads smoothly for ease of application. Using Isophthalic resins, 60701 can be used where high heat distortion temperatures are required. 60701 is catalyzed with BPO paste. It is an excellent radius compound.

GENERAL PROPERTIES:

Viscosity:	Non-flowing Paste
Catalyst:	BPO Paste
Shelf life:	6 months (stored out of sun)
Pot Life:	8 to 12 minutes with 2% BPO Paste at 76 deg. F.
Weight/Gallon:	11 to 13 pounds
Sp. Gr.:	1.32 to 1.56
Chemically:	Polyester resin and fillers

USES FOR 60701

- Power craft (OEM and repair)
- Sailboats
- Yachts
- Mobile homes
- Travel trailers
- Truck cab
- Tooling
- Most other fiberglass applications

Notice: This information is presented in good faith, but no warranty expressed or implied is given. The information, to our best knowledge, is true and accurate, but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control.

Revised April 2015

DBF, Inc. 18576 Krause PO Box 2385 Riverview, MI 48193
Phone: 734-285-1480 Fax: 734-285-1481 Website: dbf-inc.com Email: custserv@dbf-inc.com