



**80949-25**

**PRODUCT INFORMATION:**

80949-25 is a high viscosity lightweight product for use in the fiberglass industry. This product was developed to fill the needs of this industry for a low weight per gallon filler with a low exotherm and good adhesive properties. 80949-25 contains glass fibers for added strength.

**GENERAL PROPERTIES:**

Viscosity:	Stable paste non-flowing
Catalyst:	MEK Peroxide
Shelf Life:	6 months (stored out of sun)
Gel Time:	20 to 30 minutes with 1% DDM-9 at 76 deg. F
Sp. Gr.:	0.6 to 0.64
Weight/Gallon	5 to 5.3
Physical Form:	Viscous paste
Chemically:	Polyester resin and fillers
Flash Point:	Closed cup 89 deg. to 90 deg. F.

**USES FOR 80949-25:**

- Power craft
- Sailboats
- Yachts
- Mobile homes
- Travel trailers
- Truck cab
- Automotive
- Most other fiberglass applications

Notice: This information is presented in good faith, but no warranty expressed or implied is given. The information, to our best knowledge, is true and accurate, but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control.

Revised: April 2015