



90906

PRODUCT INFORMATION:

90906 is a resilient polyester compound for areas where some flexibility is required. 90906 is designed to spread easy for ease of application and ease of mixing MEK Peroxide catalyst. 90906 has excellent adhesion to fiberglass and excellent strength.

GENERAL PROPERTIES:

Viscosity:	Stable Non-flowing Paste
Shelf Life:	3 to 4 months (stored out of sun)
Pot Life:	15 to 20 minutes with 2% DDM-9 at 76 deg. F
Weight/Gallon:	5.8 to 6.2 pounds/gallon
Chemically:	Polyester resin and fillers
Flash Point:	Closed cup 89 deg. to 90 deg. F.

USES FOR 90906

- Power craft (OEM and repair)
- Sailboats
- Yachts
- Mobile homes
- Travel trailers
- Truck cab
- Tooling
- Most other fiberglass applications

Notice: This information is presented in good faith, but no warranty expressed or implied is given. The information, to our best knowledge, is true and accurate, but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control.

Revised: April 2015