



## RO61-46

### PRODUCT INFORMATION:

RO61-46 is a low viscosity product, which has been developed to fill a need for an adhesive that will flow from a 55 gallon drum and can be thickened to a heavy paste after the adhesive has been removed from the drum and before it is applied to the part. After mixing in the MEK Peroxide catalyst, the addition of a small amount of water will thicken RO61-46.

### GENERAL PROPERTIES:

Viscosity:	Thixotropic Paste
Catalyst:	MEK Peroxide
Shelf life:	6 months (stored out of sun)
Pot Life:	10 to 14 min. with 1% DDM-9 at 76° F. 30 to 60 min. with 1% DDM-9 & 1% water at 76° F.
Weight/Gallon:	13 to 14 pounds
Sp. Gr.:	1.56 to 1.68
Chemically:	Polyester resin and fillers

### USES FOR RO61-46

- Power craft (OEM and repair)
- Sailboats
- Yachts
- Mobile homes
- Travel trailers
- Truck cab
- Tooling
- Most other fiberglass applications

Notice: This information is presented in good faith, but no warranty expressed or implied is given. The information, to our best knowledge, is true and accurate, but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control.

Revised April 2015